

**Sand 0.45 - 0.55mm**  
Typical Lab Analysis

SIEVE	0.45 - 0.55 Sand
#14	100
#16	99.8
#18	99.5
#20	99
#25	82.9
#30	38.1
#35	11.2
#40	1.85
#45	0.5
Effective Size (mm)	0.49
Uniformity Coefficient	1.3
Specific Gravity	2.65
Loss on Ignition	Less than 4%
Hardness	7
Acid Solubility	0.07%